



The Plastic Films Specialist

Tenopex® TX-TCC Polyester Technical Data Sheet

Description and Applications

Tenopex® TX-TCC is a corona treated clear polyester (PET) film for optimized for screen, UV and solvent-based printing applications requiring reliable ink adhesion. Typical applications include name plate, overlay, membrane switches, release liner, insulation barrier & spacer, Label & graphics substrates, adhesive tapes etc.

Typical Property Values

Property	Test Method	Units	Value
Physical			
Density	ASTM D792	g/cm ³	1.4
Optical			
Light Transmission	ASTM D1003-61	%	87 - 90
Haze	ASTM D1003-61	%	1.2 - 1.4
Mechanical			
Tensile Strength at Break	ASTM D882	Kg/mm ²	18
Tensile Elongation at Break	ASTM D882	%	90
Friction Coefficient	ASTM D1894	Static	0.5
Thermal			
Standard Temperature Resistance	ASTM D1525-76	°C	> 105
Shrinkage at 130°C/30min	ASTM D1204	% (min)	1.5 – 2.5
Electrical			
Dielectric Strength	JIS C2151	KV/mm	300KV/mm
Dielectric Constant	JIS C2151	1KHz	3.2
		1MHz	3.0
Dissipation Factor	JIS K6911	1KHz	0.3%
		1MHz	1.2%
Volume Resistivity	JIS C2151	Ω.cm	10 ¹⁷

Tenopex Plastics Co., Ltd

Unit 101, Building 2, No. 136, Hua Xia Road Qiaotou Town,
Dongguan City, Guang Dong Province, China 523532
(86) 138 25753516 marketing@tenopexplastics-cn.cn

www.tenopexplastics.com

Global Sales Office

(852) 6888 0563 helen.koh@optimaplusgroup.com
(65) 87267516 helen.koh@optimaplusgroup.com

These are typical properties and are not intended for specifications purposes. If minimum certifiable properties are required, please contact your local sales representative. Reported values are based on 0.250mm thickness film unless otherwise noted.

Each user is responsible for making its own determination as to the suitability of Tenopex's products, services and recommendations for the user's particular use through appropriate end-use testing and analysis. Although any information or technical recommendation will be given without warranty nor guarantee nor implied, that the results indicated herein are obtained under end-use conditions. Except as provided in seller's standard conditions of sale, seller shall not be responsible for any loss resulting from any uses of its products or services described herein.