



The Plastic Films Specialist

FR42 Technical Data Sheet

Description and Applications

Tenopex®PC FR42 which has velvet/matte finish construction, is a clear translucent polycarbonate film with excellent flame retardant performance rating at UL94 V-0 at 0.25mm. The product meets critical requirements in terms of physical, mechanical, electrical and thermal properties. Besides, it has good printability, formability and dimensional stability even at high temperature. Its superior product features make it ideal for various insulation with printing applications such as computer labels, aerospace printing labels and panels, TV and monitor insulation and so on.

Typical Property Values

Property	Test Method	Units	Value
Physical			
Density	ASTM D792	g/cm ³	1.33
Water Absorption , 24hrs	ASTM D570	%	0.29
Optical			
Light Transmission	ASTM D1003	%	82
Mechanical			
Tensile Strength	ASTM D882	MPa	63
Tensile Elongation at Break	ASTM D882	%	25
Young Modulus	ASTM D882	MPa	≥2100
Impact Strength (0.76mm)	ISO 6603-1	J	31
Thermal			
Heat Deflection Temperature at 1.82Mpa	ASTM D648	°C	137
Coefficient of Thermal Expansion	ASTM D696	10 ⁻⁵ /°C	7
Coefficient of Thermal Exchange	ASTM C177	W/m.°C	0.19
Shrinkage at 150°C	ASTM D1204	%	1.4



The Plastic Films Specialist

FR42 Technical Data Sheet

Electrical

Dielectric Strength	ASTM D149	V	17000
Surface Resistivity	ASTM D257	Ω /square	10^{15}
Volume Resistivity	ASTM D257	Ω .cm	10^{16}

UL Flammability

Film thickness < 0.25mm	UL94	VTM-0
Film thickness \geq 0.25mm	UL94	V-0

Manufacturing Gauge Specifications

Nominal Gauge Ranges	Min/Max Tolerances of Nominal
0.125mm - 0.175mm	+/- 10%
0.25mm - 0.375mm	+/- 7%
0.5mm – 0.76mm	+/- 5%

These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local sales representative. Reported values are based on 0.250 mm thickness film unless otherwise noted.

Each user is responsible for making its own determination as to the suitability of Tenopex's products, services and recommendations for the user's particular use through appropriate end-use testing and analysis. Although any information or technical recommendation will be given without warranty nor guarantee nor implied, that the results indicated herein are obtained under end-use conditions. Except as provided in seller's standard conditions of sale, seller shall not be responsible for any loss resulting from any uses of its products or services described herein.