

Tenopex® TX-GW Polyester Technical Data Sheet

Description and Applications

Tenopex® TX-GW is a gloss white polyester film engineered for high quality graphic, label and overlay applications where a bright, reflective white surface and excellent print adhesion are required. It features a smooth high gloss white finish with variant of single surface or double surface treated for enhanced adhesion with solvent, UV, screen printing inks as well as laminating adhesives. TX-GW combines high whiteness, toughness and heat resistance, making it suitable for durable overlays, nameplates, backlit displays, display signage, insulation barrier, etc

Typical Property Values

Property		Test Method	Units	Value
Physical				
Density		ASTM D792	g/cm3	1.4
Color		-	Gloss White	
Thickness Tolerance		-	um	± 2 – 6
Optical				
Light Transmission		ASTM D1003-61	%	8 - 13
Mechanical				
Tensile Strength at Break	MD	GB/T 1040.3-06	MPa	> 140
	TD			
Tensile Elongation at Break	MD	GB/T 1040.3-06	%	80 - 90
	TD			
Thermal				
Standard Temperature Resistance		ASTM D1525-76	°C	> 105
Shrinkage at 130°C/30min		ASTM D1204	% (min)	0.5 – 1.5
Electrical				
Dielectric Strength		JIS C2151	V/um	60

Tenopex Plastics Co., Ltd

Unit 101, Building 2, No. 136, Hua Xia Road Qiaotou Town,
Dongguan City, Guang Dong Province, China 523532
(86) 138 25753516 marketing@tenopexplastics-cn.cn
www.tenopexplastics.com

Global Sales Office

(852) 6888 0563 helen.koh@optimaplustgroup.com
(65) 87267516 helen.koh@optimaplustgroup.com

These are typical properties and are not intended for specifications purposes. If minimum certifiable properties are required, please contact your local sales representative. Reported values are based on 0.250mm thickness film unless otherwise noted.

Each user is responsible for making its own determination as to the suitability of Tenopex's products, services and recommendations for the user's particular use through appropriate end-use testing and analysis. Although any information or technical recommendation will be given without warranty nor guarantee nor implied, that the results indicated herein are obtained under end-use conditions. Except as provided in seller's standard conditions of sale, seller shall not be responsible for any loss resulting from any uses of its products or services described herein.