



The Plastic Films Specialist

EverCore™ PVC (Digi) Core Stock Card Substrates Technical Data Sheet

Description and Applications

Evercore™ PVC (Digi) Core Stock is a premium polyvinyl chloride core stock engineered specifically for digital printing presses like HP Indigo, Konica Minolta and other alike. Featuring high impact strength and smooth matte surface, this is well suited for graphics printing, signage and laminating. EverCore™ PVC (Digi) Core Stock offers excellent flex properties, embossed character retention and color consistency making it ideal as a substrate for card manufacturing industry where longevity, durability and performance are critical.

Availability

Gauges .004" - .033"
White and customs colors
Sheets and rolls produced to specifications

Typical Applications

Bank Cards / Credit Cards / Debit Cards
Member / Loyalty / Contact / Contactless Smart Cards
ID Tags / Labels

Typical Property Values

Property	Test Method	Units	Value
Physical			
Density	ASTM D792	g/cm3	1.40 +/- 0.05
Width (TD)	-	mm	+/- 0.5mm
Length ((MD)	-	mm	+/- 0.5mm
Squareness	1m x 1m	mm/M	≤ 1.2
Dyne Level	(#4)	ISO 8296	Dyne/cm
	(#5)		Dyne/cm
Roughness (#4)	R _a	DIN 4768	um
	R _z		um
Roughness (#5)	R _a	DIN 4768	um
	R _z		um
Gloss	(#4)	-	°
	(#5)		°
Chroma	DIN 53236 / DIN 5033	-	ΔE ≤ 1.0
Mechanical			
Tensile Strength	MD	DIN EN ISO 527	MPa
	TD		MPa
Impact Strength	DIN EN ISO 8256	KJ/m ²	≥ 450
Thermal			
Shrinkage at 140°C / 10min	MD	ASTM D1204	%
	TD		%
Vicat Heat Resistance (B50)	DIN EN ISO 306	°C	78 +/- 2°C

Tenopex Plastics Co., Ltd

Unit 101, Building 2, No. 136, Hua Xia Road Qiaotou Town,
Dongguan City, Guang Dong Province, China 523532
(86) 138 25753516 marketing@tenopexplastics-cn.cn

www.tenopexplastics.com

Global Sales Office

(852) 6888 0563 helen.koh@optimaplusgroup.com
(65) 87267516 helen.koh@optimaplusgroup.com

These are typical properties and are not intended for specifications purposes. If minimum certifiable properties are required, please contact your local sales representative. Reported values are based on 0.23mm thickness film unless otherwise noted.

Each user is responsible for making its own determination as to the suitability of Tenopex's products, services and recommendations for the user's particular use through appropriate end-use testing and analysis. Although any information or technical recommendation will be given without warranty nor guarantee nor implied, that the results indicated herein are obtained under end-use conditions. Except as provided in seller's standard conditions of sale, seller shall not be responsible for any loss resulting from any uses of its products or services described herein.